

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
  - TEXT CUT OFF AT TOP, BOTTOM OR SIDES
  - FADED TEXT
  - ILLEGIBLE TEXT
  - SKEWED/SLANTED IMAGES
  - COLORED PHOTOS
  - BLACK OR VERY BLACK AND WHITE DARK PHOTOS
  - GRAY SCALE DOCUMENTS
- 

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problems Mailbox.**




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>B29D 30/00, B29C 35/08</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/13883</b> <b>(43) International Publication Date:</b> 16 March 2000 (16.03.00)
<b>(21) International Application Number:</b> PCT/US98/18520 <b>(22) International Filing Date:</b> 4 September 1998 (04.09.98) <b>(71) Applicant (for all designated States except US):</b> THE GOODYEAR TIRE & RUBBER COMPANY [US/US]; 1144 East Market Street, Akron, OH 44316-0001 (US). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> PRAKASH, Amit [IN/US]; 105 Keswick Drive, Hudson, OH 44236 (US). WOODS, Terry, Kenneth [US/US]; 6939 Eastham Circle, Canton, OH 44708 (US). REESE, David, Thomas [US/US]; 3215 Brooklawn Drive, Norton, OH 44203 (US). VANNAN, Frederick, Forbes, Jr. [US/US]; 8509 Foxglove Avenue, Northwest, Clinton, OH 44216 (US). <b>(74) Agent:</b> KING, David, L.; The Goodyear Tire & Rubber Company, Dept. 823, 1144 East Market Street, Akron, OH 44316-0001 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>

**(54) Title:** INDUCTION CURABLE TIRE COMPONENTS AND METHODS OF SELECTIVELY CURING SUCH COMPONENTS**(57) Abstract**

A rubber tire component (10, 20, 30, 40) laden with a mixture of fibers (12). The fibers (12) being sensitive to induction heating can be rapidly cured using a variety of methods. The preferred method permits a selective induction curing of the fiber laden component (10, 20, 30, 40) in combination with conventional curing presses.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INDUCTION CURABLE TIRE COMPONENTS AND METHODS  
OF SELECTIVELY CURING SUCH COMPONENTS

5    Technical Field

        This invention relates to the vulcanization and bonding of tire components, more particularly it relates to the use of induction heating to assist in the curing or bonding of said tire components.

10   Background Art

        Generally tires are cured in a process known as vulcanization whereby elastomeric material is heated in molds. The heated molds are generally conductive in nature and transfer heat from the surface of the tire to the internal components  
15    requiring a fixed amount of time at a given temperature in order to achieve full complete curing of the tire.

        Rubber or elastomeric material is not an effective conductive material and acts as somewhat of an insulator. Therefore, for a complete curing of a tire to occur, many of the  
20    components are over cooked or exposed to a larger amount of heat than normally would be required if the tire would quickly and uniformly achieve curing temperature. Due to the various time lengths involved in the curing process to bring all of the material up to curing temperature the vulcanization process  
25    requires many minutes to completely cure a tire. In European patent publication 0183450A2, Anthony James Sumner devised a mold which would permit a tire to be cured using electric current which may be induced electromagnetically. The mold itself had a variety of insulating segments and side plates  
30    which permitted varying amounts of conductive heat to be applied to the mold in such a fashion that selective regions of the tire could achieve more heat in such areas where the tread and bead are thicker. The mold itself was a rather complicated structure which did permit an electromagnetic curing of the entire tire  
35    structure. The mold however provided the selective curing capability of the tire for thick and thin regions.

In U.S. Patent No. 5,483,043 assigned to General Electric Company, inducting heat of polymer matrix composites mold press was disclosed wherein electrically conductive fibers were added to the polymer matrix to facilitate the induction heating of the polymer. This patent deals with polymeric matrix that generally fall into two classes, thermosetting and thermoplastic which are fiber loaded. Examples of materials typically for reinforcing fibers include carbon graphite, boron, and silicon carbide. It is believed that the polymeric components manufactured under General Electric Company's patent related to the aircraft industry and did not include nor encompass rubber tire components.

In a Japanese patent application more relevant to the rubber industry Patent No. JP8216289A discloses a method of retreading tires using high frequency waves to vulcanize the adhesive layer incorporating the base tire with the reheating member. In this patent the steel cords in the belt layers are heated by activating or inducing an inductive heating coil which heats the steel cords and in turn provides a heat source for the curing of the cushion gum used in the retreading of the tire. While this method of using induction heating provides the use of the tire cords as the inductively heated metal component it is recognized that such cords have limited surface area and the heat transfer is rather localized around the belt cords.

It is an object of the present invention to find a uniform dispersal of fibers susceptible to inductive heating throughout a tire component so that the tire can be selectively cured. It is a further object of the invention to provide a preformed rubber component having fibers which are susceptible to inductive heating that will permit the tire to be more rapidly cured when used in combination with conventional curing methods.

### Summary of the Invention

A method of selectively curing tire components (10, 20, 30, 40) has the steps of dispersing a plurality of metal particles (12) or filaments (12) into a rubber composition (14).

5 Preferably, the dispersion of the plurality of metal particles (12) or filaments (12) into a rubber composition (14) includes the step of extruding the material while blending in the fibers (12) or metal particles (12).

The fiber loaded rubber composition is then preshaped into  
10 a tire component (10, 20, 30, or 40) of a predetermined cross-section. Then the tire component can be placed in an induction heating coil and the heating coil can be activated thereby internally curing the tire component while maintaining the external surfaces of the tire component partially or completely  
15 uncured.

In order to achieve this selective curing of tire components, it is further contemplated that one would preselect a time and energy profile for a particular tire component to insure the external components remain at least initially uncured  
20 while the interior of the tire component is cured.

Several alternative methods of selectively curing tire components (10, 20, 30, or 40) further have the steps of placing the preshaped tire component with fiber or metal particles (12) disposed throughout into an assembly of tire components prior to  
25 applying induction heating. The entire tire assembly (2) is then placed in an induction coil which is activated thereby heating the fiber laden component and then after curing or partially curing that component (10, 20, 30, or 40), one finishes the curing of the tire assembly (2) in a conventional  
30 mold curing press.

Alternatively, the placing of the preshaped fiber loaded tire component into an assembly (2) of tire components prior to applying induction heating can include the step of placing the

tire assembly (2) in a conventional curing press and curing all the uncured external surfaces of the tire (2) and then placing the tire (2) in an induction coil and applying induction heating to finish cure the preshaped tire component or components (10, 20, 30, or 40). In another method, the preshaped tire components loaded with fibers or metallic particles (12) can be assembled within an assembly of other tire components prior to applying induction heating and then placing the entire tire assembly (2) in a mold curing press and simultaneously providing conductive and induction heating to cure the tire components and the tire assembly in a single curing process.

In a preferred embodiment of the invention, the preshaped component will be premixed with induction sensitive particles (12) such as iron, nickel, oxides of iron, nickel, etc. When such fibers (12) are loaded into a rubber compound (14) and dispersed through an extrusion process or some other method, as little as a fraction of one percent to five percent of fiber (12) per 100 parts by weight of rubber is needed in order to achieve a high dispersion of induction sensitive material throughout the composition. This minimal amount of fibers (12) enables the component (10, 20, 30, or 40) to be rapidly heated thus permitting the selective curing described above.

#### **Brief Description of Drawings**

The invention may take physical form in certain parts and arrangement of parts a preferred embodiment of which will be described in detail in this specification and illustrated in the accompanying drawings which form a part hereof and herein:

FIGURE 1 is a cross-sectional view of a apex tire component (10) preformed of elastomeric material laden with induction sensitive particles or fibers (12).

FIGURE 2 is a cross-sectional view of a sidewall insert tire component (20) preformed and laden with induction sensitive particles or components.

FIGURE 3 is a strip of tread rubber (30) laden with induction sensitive particles or fibers (12).

FIGURE 4 is a strip of cushion gum rubber tire component (40). The cushion gum rubber is laden with induction sensitive particles or fibers, the cushion gum being used as a component between the tread and a tire casing.

FIGURE 5 is a cross-sectional view of a portion of a tire assembly (2) and one embodiment of the electric induction heating means (6) according to the invention.

FIGURE 6 is a cross-sectional view of a tire assembly (2) placed in a curing mold (8) having a plurality of induction coils (6) placed around the periphery of the tire mold (8).

#### Detailed Description of the Invention

FIGURES 1-4 show various tire components made of elastomeric material laden with induction sensitive particles or fibers (12). The tire components include but are not limited to a rubber apex (10) having a predetermined cross-section, a sidewall insert (20) for runflat tires having a predetermined cross-section, a tread strip (30) and cushion gum layer (40) also having a predetermined cross-section. Each of these components can be provided in strips of unvulcanized rubber. The rubber being laden with induction heat sensitive particles or fibers (12). The preferred method is to premix the induction sensitive particles or fibers (12) in the rubber compound (14) prior to shaping the component (10, 20, 30, 40). It is believed preferable that extrusion should be used to premix the induction sensitive particles (12) and to disperse them throughout the component.

In the tire art the entire rubber product is generally cured by the addition of general heating from a surrounding heat source. There is no control over the amount of heating or the duration of heating that each individual component receives. In this invention, each fiber laden component (10, 20, 30, or 40)



can receive a specific amount of heating for a specific duration exclusive of other components. This is possible because when the induction coil is energized the particles heat very rapidly. Therefore, an induction coil can sensitize the particles (12) in various locations of the tire (2) and create a specific amount of heat for a specific duration. These predetermined heating and time exposures can assist in the rapid curing of the tire (2) particularly in the large thick sections of the tire which historically were difficult to cure.

10 In order to achieve optimum induction heating of the component it is believed preferable to use sensitive materials such as iron, nickel, oxides of iron or nickel or other induction sensitive materials. In experiments when nickel fibers or iron oxide fibers were provided in rather small quantities just a few percent throughout the rubber (14) and placed into an induction coil which is energized the rubber component exhibited an increase in temperature as the coil was activated. This increase in temperature was sufficient to provide a curing affect for the component. This form of heating of the component fundamentally provided an internal rapid heating of the tire component such that internal curing or vulcanization of the tire component could be achieved while maintaining the outer or peripheral surfaces of the component green or substantially uncured. This ability to cure internally a component enables the tire designer to provide a part that otherwise would inhibit rapid conventional curing of a tire.

Once the tire component is premixed with the induction sensitive particles several methods of curing the tire are possible. As noted the component can be partially precured internally prior to placing the component in a tire assembly (2). Then the precured component can be finish cured in a conventional manner. An alternative method is to place the preshaped tire component laden with induction sensitive

particles into an assembly (2) of tire components prior to applying induction heating, then placing the tire assembly (2) in a curing press and curing all uncured external surfaces of the tire (2) and then placing the tire (2) in an induction coil and applying induction heating to finish cure the preshaped tire components (10, 20, 30 or 40). Another alternative is to reverse the sequence and place the preshaped component into an assembly of tire components prior to applying to induction heating then placing the tire assembly in an induction coil and applying induction heating and then finish curing the tire assembly (2).

A final alternative is to place the preshaped tire components laden with induction sensitive particles or fibers (12) into an assembly of tire components and then simultaneously apply induction heating and conventional curing to the tire (2). In all of the above cases it is believed that the amount of time for conventional curing is dramatically reduced by the use of induction heating of the internal components.

One of the most beneficial aspects of the use of induction heating can be to prepare a rubber cushion (30) unvulcanized laden with induction sensitive particles that can be placed between the tread (30) of a tire (2) and the casing (3). In this case, as shown in FIGURE 5, the tread (30) can be precured and the casing (3) precured. This is very similar to the methods used in retreading commercial truck tires but is equally applicable to new tire production. In such a case the bonding or joining of the tread (30) to the casing (3) is achieved by applying an induction current to the cushion gum (40) exciting the induction sensitive particles to generate a rapid heating of the cushion gum layer which quickly vulcanizes the cushion gum and creates a joint between the tire (2) and the casing (3).

It is believed by using induction heating in this fashion, commercial truck tires can be made or retreaded in a matter of

minutes greatly reducing the time to cure the retreaded tire or new tire.

An alternative method to preparing a preshaped cushion gum is provide the cushion gum (40) in an adhesive form which is a liquid coating (40) laden with particles sensitive to induction heating. In such a case a thin coating on the under side of the tread (30) and on the crown of the casing (3) can be applied, the thin coating (40) or adhesive being laden with this induction sensitive particles upon assembly can be placed into an induction coil which is initiated which will then create a joint between the two adhesive layers, thus, bonding the tread (30) and the casing (3).

In all of the above-mentioned method of preparing an induction laden mixture of unvulcanized rubber and induction sensitive particles or fibers it should be noted that only a small amount of material is needed in the range of a fraction of one percent or two of fibers per 100 parts of rubber. These fibers are sufficiently small to enable the tire designer to implement them into almost any component without degrading the material in terms of its overall performance characteristics. In fact, in many cases the short fibers that are induction sensitive increase the stiffness of the tire component and can be used to help strengthen the component if needed. In those cases higher percentages of induction laden components can be used to enhance the performance of the tire component. It is believed possible to add up to five percent of material when added strength is needed. While as little as .01% of induction sensitive particles are fibers per 100 parts of rubber can be employed as noted 5% or less induction sensitive particles or fibers per 100 parts of rubber can be used. While the preferred embodiment discloses the use of a preshaped elastomeric tire component as an intermediate article of manufacture having a rubber composition having a mixture of induction sensitive

particles or fibers (12), it is also noted that the material can be unvulcanized elastomeric tire adhesive of a liquid or semi-liquid composition having a rubber mixture having induction sensitive particles or fibers (12). It is also believed  
5 preferred that the induction sensitive particles or fibers (12) be metallic. Most preferably the metallic fibers (12) should be of nickel or iron based material.

As shown in FIGURE 5, a cross-sectional view of the entire tire assembly (2) is shown along with an electric induction  
10 heating means (6).

As further shown in FIGURE 6, a cross-section view of the tire assembly (2) in a tire curing mold (5) with a plurality of induction heating coils (6) around the periphery of the mold (5) is shown. Each FIGURE 5 and 6 show means for accomplishing the  
15 desired curing methods described above.

It is understood that the invention can be utilized on almost any tire component but is most preferable in components having a thick cross-section or that are internally buried within the tire. It is also preferable that the tire component  
20 can simply be a bonding layer between two tire components such as a tread and tire casing as described above or alternatively can take the form of an adhesive.

The preferred embodiment of the invention has been described herein above. It will be apparent to those skilled in  
25 the art that the above methods may incorporate changes and modifications without departing from the general scope of this invention. It is intended to include all such modifications and alterations insofar as they come within the scope of the appending claims or the equivalence thereof.

## CLAIM

1. A method of selectively curing tire components comprising the steps of:

dispersing a plurality of metal particles or filaments  
5 into a rubber composition;  
preshaping the rubber composition into a tire component of a predetermined cross-section;

placing the tire component in an induction heating coil  
applying induction heating by activating the induction heating  
10 coil thereby internally curing the tire component while maintaining the external surfaces of the tire component partially or completely uncured.

2. The method of selectively curing tire components further comprising the steps of:

15 preselectively a time and energy profile for the tire components to insure the external surfaces remain at least partially uncured while the interior of the tire component is cured.

3. The method of selectively curing tire components of claim 1 further comprises:

placing the preshaped tire component into an assembly of tire components prior to applying induction heating;

placing the tire assembly in an induction coil and applying induction heating; and,

25 then finish curing the tire assembly.

4. The method of selectively curing tire components of claim 1 further comprising:

placing the preshaped tire component into an assembly of tire components prior to applying induction heating;

30 placing the tire assembly in a curing press and curing all uncured external surfaces of the tire; and then,

placing the tire in an induction coil and applying induction heating to finish cure the preshaped tire components.

5. The method of selectively curing tire components of claim 1 further comprises:

placing the preshaped tire components into an assembly of tire components prior to applying induction heating;

5 placing the tire assembly in a mold curing press and simultaneously provide conductive heating and induction heating to cure the component and the tire assembly.

6. A unvulcanized elastomeric tire component, as an intermediate article of manufacture having a predetermined  
10 cross-sectional shape, the tire component characterized by:

a rubber composition having a mixture of induction sensitive particles or fibers.

7. The unvulcanized elastomeric tire component of claim 6 further characterized by at least 0.01% of induction sensitive  
15 particles or fibers per 100 parts of rubber.

8. The unvulcanized elastomeric tire component of claim 7 further characterized by 5% or less induction sensitive particles or fibers per 100 parts of rubber.

9. The unvulcanized tire component of claim 6 wherein the  
20 induction sensitive particles or fibers are metallic.

10. An unvulcanized elastomeric tire adhesive of a liquid or semi-liquid composition, the tire adhesive characterized by:

a rubber mixture having induction sensitive particles or fibers.

1/3




FIG-1




FIG-2




FIG-3




FIG-4

2/3




FIG-5



3/3




FIG-6

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 98/18520

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 6 B29D30/00 B29C35/08

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B29D H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 098, no. 010, 31 August 1998 & JP 10 128764 A (SUMITOMO RUBBER IND LTD), 19 May 1998	1,6,10
Y	see abstract ---	2,3
Y	US 3 933 566 A (SEIBERLING THEOPHILUS K) 20 January 1976	2,3
A	see column 2, line 48 - column 3, line 30 ---	4,5
X	DATABASE WPI Section Ch, Week 9809March 1998 Derwent Publications Ltd., London, GB; Class A35, AN 98-090072'09! XP002102531 & JP 09 207241 A (SUMITOMO RUBBER IND LTD) , 12 August 1997	6-9
Y	see abstract; figures ---	10

-/-

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

12 May 1999

Date of mailing of the international search report

27/05/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Mathey, X

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/18520

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 503 794 A (MINNESOTA MINING & MFG) 16 September 1992 see claims 1,12,19,20,42 ---	10
A	FR 2 224 286 A (GOODYEAR TIRE & RUBBER) 31 October 1974 see the whole document -----	2-5

# INTERNATIONAL SEARCH REPORT

Information on patent family members

In tional Application No

PCT/US 98/18520

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3933566 A	20-01-1976	US 3933553 A	20-01-1976
		US 4851063 A	25-07-1989
EP 0503794 A	16-09-1992	AU 656556 B	09-02-1995
		AU 1110292 A	17-09-1992
		AU 671014 B	08-08-1996
		AU 6311494 A	21-07-1994
		JP 5140530 A	08-06-1993
		US 5529708 A	25-06-1996
		US 5837088 A	17-11-1998
FR 2224286 A	31-10-1974	AR 203554 A	22-09-1975
		AT 334762 B	10-02-1976
		AT 204174 A	15-05-1976
		AU 6665174 A	18-09-1975
		BE 812137 A	01-07-1974
		CH 579977 A	30-09-1976
		DD 112386 A	12-04-1975
		DE 2411267 A	24-10-1974
		GB 1448532 A	08-09-1976
		JP 50003182 A	14-01-1975
		LU 69665 A	10-07-1974
		NL 7404636 A	11-10-1974
		PH 14365 A	17-06-1981
		TR 18214 A	01-03-1977
		ZA 7401629 A	26-02-1975